



**Adhesives &
Fastening Products**

355 Hollow Hill Drive
Wauconda, IL 60084
Ph: 847.487.4583
Fax: 847.487.0174
E-mail: glueguns@aol.com
www.surebonder.com

**Specification Sheet
862**

Type: Hot Melt Adhesive
Viscosity ¹: 4000 cps @ 260°(F)
Open Time: 15 Seconds
R & B Softening Point: 195° (F)
Color: Light Amber
Odor: Slight
Shelf Life: Indefinite
Flash Point: Above 450° (F)

Storage: Common Storage

Application Temperature: 250° (F) to 300° (F)

Common Applications: Low temperature packaging adhesive with excellent hot tack, short open time and good delivery rate. Good adhesion to plain and some coated corrugated packaging, paper products, wood and foam. Fast Set

Precautions: Do Not Mix with other adhesives.
Severe burns will result if contact is made in molten state.
Material safety data sheets provide safety precautions that should be observed in handling and storing.

The buyer should conduct it's own tests of this product before use to determine proper preparation technique and suitability for proposed application. FPC warrants that the product conforms with FPC written specifications, and is free from defects. FPC disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.

¹ Brookfield Viscosity – ASTM D3236

² R & B Softening Point –ASTM E28