



# CONCRETE SAVER®

## FLEXIBLE JOINT SEALANT

### DESCRIPTION AND USES

Rust-Oleum® Flexible Joint Sealant is a two-component, rapid curing, 1:1 ratio, self leveling, 100% solids, flexible system that provides 10-15% movement of installed joint width. This product can be used at temperatures between -40 to 120°F (-40 to 49°C).

Flexible Joint Sealant is used to fill interior control joints or new construction saw cuts on horizontal concrete surfaces. It is designed for industrial floor applications receiving heavy duty vehicle traffic. Flexible Joint Sealant can be used for interior expansion joints with the maximum joint width not to exceed one inch. It can be used on exterior applications when minimal joint movement from thermal cycling will occur. Joints can be opened to traffic in 90 minutes at 72°F (22°C).

### PRODUCTS

SKU	DESCRIPTION
261998	9 oz. Flexible Joint Sealer
266733	22 oz. Flexible Joint Sealer

### COMPANION PRODUCTS

SKU	Description
257397	Replacement Static Mixer Nozzle (3 per pack)
261292	Caulk Gun (9 oz.)

### PRODUCT APPLICATION

#### JOINT PREPARATION

Remove all dust, debris, oil and any other contamination from the construction and/or saw cut joints. For best results re-cut the joints with a dry diamond blade. Joints must be clean and dry. Fill deep cracks with backer rod before applying the joint sealant. The minimum depth of the joint should be twice the width with a minimum depth of ½ inch. Dispense material into joint so that material is slightly higher than the face of the concrete. Allow the product to set for approximately 45-90 minutes at 75° F. Then use a sharp razor scraper to shave excess material from top of slab.

**LIMITATIONS:** Floor Joint Sealant is not intended for joints that are subject to high movement on exterior applications. This is a moisture sensitive product during and prior to full cure. Joints must be clean and dry to facilitate a strong bond.

Note: 22 oz Flexible Joint Sealant comes in a side by side dual component cartridge. It is compatible with any standard 22 oz. dispensing tool.

### PRODUCT APPLICATION (cont.)

#### CARTRIDGE SET-UP

**IMPORTANT:** Shake cartridge vigorously for 1 minute, then stand cartridge upright for 1 minute. During set-up of cartridge and initial dispensing of material, keep cartridge and nozzle assembly pointed straight up. AFTER the initial shot of material, do not point the cartridge upward to prevent material in nozzle from flowing back into cartridge.

The two components are supplied in a dual cartridge and mixed simultaneously through a static mixing nozzle. While preparing cartridge for dispensing, keep cartridge in upright position to prevent material from leaking out of cartridge. Do not tilt cartridge until material is ready to be applied to the repair area.

#### APPLICATION

Insert cartridge into dispenser. Make sure it is properly positioned with shoulder of cartridge flush with front/top bracket of the dispenser. Remove plastic cap from the top of the cartridge. Place the mixing nozzle onto the cartridge and secure by threading in a clock-wise direction. Make sure that the nozzle and cartridge assembly is secure. Point nozzle straight up and slowly apply pressure to the dispenser, moving product up and through the nozzle until it reaches the tip. Then dispense 1 stroke of material into a rag or disposable container (1-2 quick bursts if using an air tool) and discard. After purging keep the cartridge pointed downward or horizontal to prevent mixed material in the nozzle from flowing back into the cartridge.

Place the mixing nozzle directly over the crack, joint, or repair area. Dispense material using full smooth trigger pulls (no short choppy strokes) and allow material to gravity feed into the crack/joint. Fill the crack/joint or over-fill the crack/joint so that material is slightly higher than the face of the concrete slab you are repairing. Allow the product to set for approximately 45-90 minutes (at 75°F) and then use a sharp razor scraper to shave excess material from the top of slab.



## CONCRETE SAVER®

## FLEXIBLE JOINT SEALANT

## PRODUCT APPLICATION (cont.)

FOR SOLVENT-BASED TOPCOATS - You MUST wait a minimum of 24 hours prior to priming. A premium water-based primer that is compatible with solvent-based coatings, such as Zinsser® Bulls-Eye 1-2-3® or XIM® UMA® Advanced Technology Primer•Sealer•Bonder must be used prior to the application of a solvent-based topcoat.

FOR ALL OTHER TOPCOATS- Wait a minimum of 4 hours before priming or top coating.

## CLEAN-UP

Clean up immediately with xylene. Rust-Oleum 160 Thinner or MEK may be substituted.

## PERFORMANCE CHARACTERISTICS

## SHORE A HARDNESS

METHOD: ASTM D2240  
RESULT: 75-80

## TENSILE STRENGTH (@ 7 DAYS)

METHOD: ASTM D412  
RESULT: 1200 psi (8.3 MPa)

## ELONGATION (@ 7 DAYS)

METHOD: ASTM D412  
RESULT: 82%

## ADHESION TO CONCRETE (@ 7 DAYS)

METHOD: ASTM 4541  
RESULT: 275 psi (1.9 MPa)

## VISCOSITY

METHOD: ASTM D2196  
RESULT: Part A: 600 cp  
Part B: 460 cp

## BOND STRENGTH

METHOD: ASTM C882  
RESULT: 400 PSI (2.76 MPa)

## COVERAGE\*

JOINT SIZE	LINEAR FEET (9 oz.)	LINEAR FEET (22 oz.)
1/8"x1"	10.3	26.7
1/8"x1 1/4"	8.3	21.3
1/8"x1 1/2"	6.9	17.8
1/8"x1 3/4"	5.9	15.2
3/16"x3/4"	9.2	23.7
3/16"x1	6.9	17.8
3/16"x1 1/4"	5.5	14.2
3/16"x1 1/2"	4.6	11.9
3/16"x1 3/4"	3.9	10.2
1/4"x1"	5.2	13.3
1/4"x1 1/4"	4.1	10.7
1/4"x1 1/2"	3.4	8.9
1/4"x1 3/4"	3.0	7.6
1/2"x1"	2.6	6.7

\*This table gives rough guidelines on estimating the amount of material needed. These numbers represent the length of joint that can be filled with one 9 oz. or one 22 oz cartridge of material, based on the joints' width and depth.



# CONCRETE SAVER®

## FLEXIBLE JOINT SEALANT

### CHEMICAL RESISTANCE

CHEMICAL (REAGENT)	RECOMMENDED FOR CONTINUOUS SERVICE	LIMITED RECOMMENDATION (OCCASIONAL SPILLS)
Acetic Acid (10%)	X	
Acetone		X
Bleach		X
Bleach (10%)	X	
Citric Acid (5%)	X	
Crude Oil	X	
Motor Oil		X
Gasoline		X
Diesel Fuel	X	
Skydrol		X
Hydraulic Oil	X	
Ethylene Glycol		X
Fatty Acids	X	
Water (Room Temperature)	X	
NaCl (10%)	X	
Hydrochloric Acid (10%)	X	
Lactic Acid (5%)	X	
Nitric Acid (1%)	X	
Methyl Ethyl Ketone		X
Phosphoric Acid (10%)		X
Sodium Hydroxide (20%)	X	
Sulfuric Acid (20%)	X	
Toluene		X
Urea (50%)	X	
Vinegar	X	
Xylene		X

**CRACK REPAIR****TECHNICAL DATA****CS-34****CONCRETE SAVER®  
FLEXIBLE JOINT SEALANT****PHYSICAL PROPERTIES**

		FLEXIBLE JOINT SEALANT		
<b>Resin Type</b>		Two Component Polyurea		
<b>Color</b>		"A" Component (ISO) – Amber	"B" Component (Poly) – Gray	Mixed – Concrete Gray
<b>Solids</b>	<b>By Weight</b>	100%		
	<b>By Volume</b>	100%		
<b>Volatile Organic Compounds</b>		1.72 g/l (0.014 lbs./gal.) MIXED		
<b>Practical Coverage (22 oz. cartridge)</b>		1/4" joint x 1" depth; 13.3 feet		
<b>Dry Times @ 70-80°F (21-27°C) and 50% Relative Humidity<sup>†</sup></b>	<b>Gel Time</b>	3 minutes		
	<b>Tack Free Time</b>	45-90 minutes		
	<b>Shave "Window"</b>	45-90 minutes to 24 hours		
	<b>Traffic Ready Time</b>	Light Traffic/Topcoat: 90 minutes Heavy Traffic: 12-16 hours		
<b>Storage Stability</b>		Unopened containers at 60-90°F		
<b>Safety Information</b>		For additional information, see SDS		

<sup>†</sup>Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation  
11 Hawthorn Parkway  
Vernon Hills, Illinois 60061

Phone: 877-385-8155  
[www.rustoleum.com/industrial](http://www.rustoleum.com/industrial)

Form: GDH-379  
Rev.: 032723